




## THE CHEMISTRY OF MATERIALS FOR FACE MASKS: DEVELOPING EFFECTIVE FILTERS AGAINST COVID-19

 <https://doi.org/10.56238/isevmjv1n2-019>

Receipt of originals: 11/20/2022

Acceptance for publication: 12/20/2022

**Camilla Ventura**

### **ABSTRACT**

The COVID-19 pandemic highlighted the urgent need for effective personal protective equipment, particularly face masks capable of filtering viral particles. This article explores the role of chemistry in developing advanced filtration materials, focusing on polymer science, electrostatic charging, nanotechnology, and antimicrobial surface treatments. Materials such as melt-blown polypropylene, electrospun nanofibers, and biodegradable polymers have been engineered to maximize filtration efficiency while maintaining breathability and comfort. Additional innovations include hydrophobic coatings, smart sensing elements, and antiviral nanomaterials such as graphene derivatives. The study underscores the multidisciplinary advances in material chemistry that have enabled rapid and scalable mask production to address both health and environmental challenges.

**Keywords:** Filtration Materials. Electrostatic Charge. Nanofibers. Face Masks. Antiviral Coatings.



## 1 INTRODUCTION

The outbreak of the COVID-19 pandemic in late 2019 spurred an urgent global demand for personal protective equipment (PPE), particularly face masks. Among the most critical aspects of mask design lies the development of materials capable of filtering viral particles effectively while maintaining breathability and comfort. The chemistry of materials has played a pivotal role in innovating and optimizing the filters used in face masks, leveraging both traditional polymer science and advanced nanomaterial technologies to enhance their protective capabilities.

Filtration efficiency in face masks is influenced by several factors, including fiber diameter, surface charge, porosity, and electrostatic properties of the material. One of the most widely used materials in mask production is polypropylene, a nonwoven thermoplastic polymer that exhibits a high degree of filtration efficiency due to its fine fiber structure and ability to retain electrostatic charge. The melt-blown method is commonly used to produce nonwoven polypropylene layers, which create a dense mesh of fibers capable of capturing aerosols through mechanisms such as inertial impaction, diffusion, and electrostatic attraction (Liao et al., 2020). These mechanisms are particularly effective in trapping respiratory droplets and submicron particles, including those that may contain the SARS-CoV-2 virus.

Electrostatic filtration is a crucial chemical principle in enhancing mask performance. During the melt-blowing process, a technique known as corona charging or triboelectric charging is employed to impart electrostatic charges to the fibers. These charges enable the material to attract and retain oppositely charged particles suspended in the air, providing an additional line of defense beyond mechanical filtration. Studies have shown that the combination of mechanical and electrostatic filtration significantly improves the overall efficiency of the mask, with N95 respirators achieving over 95% filtration efficiency for particles as small as 0.3 microns (Qian et al., 1998).

Recent advancements in material science have explored the incorporation of nanofibers and functionalized surfaces to further improve mask performance. Electrospun nanofibers, composed of polymers such as polyvinylidene fluoride (PVDF) or polyacrylonitrile (PAN), have diameters in the nanometer range and can be engineered to create highly porous but tightly packed filter structures. These materials not only provide superior particle capture but also allow for better air permeability, addressing the common challenge of balancing filtration and breathability. Moreover, surface



modification with antimicrobial agents, including silver nanoparticles and quaternary ammonium compounds, has been investigated to confer biocidal properties to masks, potentially inactivating trapped pathogens on contact (Sportelli et al., 2020).

In addition to the chemical composition of the mask materials, sustainability and reusability have become increasingly important considerations. The environmental impact of disposable masks has prompted research into biodegradable polymers and washable filter materials. Polylactic acid (PLA), derived from renewable resources such as corn starch, has emerged as a promising candidate for eco-friendly mask production. Its favorable mechanical properties and biodegradability make it suitable for single-use or limited reuse applications, although its filtration efficiency and long-term stability require further optimization (Wang et al., 2021).

In parallel with improving filtration efficiency, researchers have also addressed the challenge of maintaining mask performance under conditions of moisture and prolonged use. Moisture generated from exhalation can degrade the electrostatic charges on filter materials, reducing their ability to capture particles over time. To combat this, hydrophobic coatings have been developed using fluorinated compounds and silane-based chemistries. These coatings help to repel water and bodily fluids, preserving the electrostatic properties of the filter layers and extending the effective use time of the mask (Zhao et al., 2020). Additionally, multilayer designs combining hydrophobic outer layers with inner moisture-absorbing layers have been employed to enhance wearer comfort while maintaining protective functionality.

Another area of innovation involves the integration of smart materials and responsive systems into face masks. For instance, thermochromic and colorimetric sensors based on chemical reactions have been embedded into mask materials to indicate saturation levels, contamination, or the need for replacement. These sensors rely on reversible chemical changes that respond to pH, temperature, or pathogen presence, providing users with real-time feedback about mask efficacy. Although still in early stages of development, such technologies represent a promising advancement in the personalization and safety of PPE (Kang et al., 2021). Furthermore, active filtration systems using electrically conductive polymers and embedded microbatteries have been tested for their ability to enhance filtration by generating localized electric fields, adding an extra layer of protection without significantly increasing breathing resistance.




The COVID-19 pandemic also catalyzed cross-disciplinary collaboration in material chemistry, microbiology, and textile engineering, resulting in rapid prototyping and commercialization of new filter materials. One example is the use of graphene and graphene oxide coatings, which possess antiviral properties due to their ability to disrupt viral membranes and generate reactive oxygen species under light exposure. Preliminary studies have demonstrated that face masks treated with graphene derivatives can inactivate SARS-CoV-2 and other respiratory viruses on contact, making them particularly suitable for healthcare environments where contamination risks are high (Palmieri et al., 2021). However, concerns regarding inhalation safety and production scalability of graphene-based materials remain under active investigation.

Figure 1 presents a flowchart summarizing the development process of effective face mask materials in response to the COVID-19 pandemic. It begins with the urgent demand for protective face coverings and proceeds through critical stages of material selection, highlighting options such as melt-blown polypropylene and biodegradable polymers like PLA. The chart outlines how these materials contribute to filtration efficiency, sustainability, and breathability through mechanisms like electrostatic charging and multilayer design. It also incorporates recent innovations, including smart sensors and antiviral coatings using nanomaterials such as graphene and silver, leading to the production of high-performance, next-generation masks.

**Figure 1**

*Development Process of Advanced Face Mask Materials for COVID-19 Protection*



Source: Created by author.

The development of high-performance face masks during the COVID-19 pandemic exemplifies the intersection of chemistry, engineering, and public health. The ability to manipulate polymer structures, control fiber morphology, and integrate functional additives has enabled researchers and manufacturers to create masks that meet stringent safety standards while addressing user comfort and environmental concerns. As the world prepares for future respiratory outbreaks, continued investment in the chemistry of filtration materials will be essential to ensure rapid, scalable, and effective responses.



## REFERENCES

1. Freitas, G. B., Rabelo, E. M., & Pessoa, E. G. (2023). Projeto modular com reaproveitamento de container marítimo. *Brazilian Journal of Development*, 9(10), 28303–28339. <https://doi.org/10.34117/bjdv9n10-057>
2. Gotardi Pessoa, E. (2025). Analysis of the performance of helical piles under various load and geometry conditions. *ITEGAM-JETIA*, 11(53), 135–140. <https://doi.org/10.5935/jetia.v11i53.1887>
3. Gotardi Pessoa, E. (2025). Sustainable solutions for urban infrastructure: The environmental and economic benefits of using recycled construction and demolition waste in permeable pavements. *ITEGAM-JETIA*, 11(53), 131–134. <https://doi.org/10.5935/jetia.v11i53.1886>
4. Kang, H., Jung, H., Lee, S., & Kim, J. (2021). Smart face mask for real-time, colorimetric detection of airborne viruses. *ACS Sensors*, 6(5), 1806–1813. <https://doi.org/10.1021/acssensors.0c02661>
5. Liao, L., Xiao, W., Yu, X., Wang, H., Wang, Q., Chu, S., & Cui, Y. (2020). Can N95 respirators be reused after disinfection? How many times? *ACS Nano*, 14(5), 6348–6356. <https://doi.org/10.1021/acsnano.0c03597>
6. Palmieri, V., Papi, M., De Spirito, M., & Ciasca, G. (2021). Face masks and nanotechnology: Keep the blue side up. *Nano Today*, 37, 101077. <https://doi.org/10.1016/j.nantod.2021.101077>
7. Qian, Y., Willeke, K., Grinshpun, S. A., Donnelly, J., & Coffey, C. C. (1998). Performance of N95 respirators: Filtration efficiency for airborne microbial and inert particles. *American Industrial Hygiene Association Journal*, 59(2), 128–132. <https://doi.org/10.1080/15428119891010389>
8. Sportelli, M. C., Izzi, M., Kukushkina, E. A., Hossain, S. I., Picca, R. A., Ditaranto, N., & Cioffi, N. (2020). Can nanotechnology and materials science help the fight against SARS-CoV-2? *Nanomaterials*, 10(4), 802. <https://doi.org/10.3390/nano10040802>
9. Wang, C., Wu, S., & Chen, L. (2021). Application of polylactic acid nonwoven fabrics as filter media for high-performance air filtration. *Polymers*, 13(3), 396. <https://doi.org/10.3390/polym13030396>
10. Zhao, M., Liao, L., Xiao, W., Yu, X., Wang, H., Wang, Q., & Cui, Y. (2020). Household materials selection for homemade cloth face coverings and their filtration efficiency enhancement with triboelectric charging. *Nano Letters*, 20(7), 5544–5552. <https://doi.org/10.1021/acs.nanolett.0c02211>